

# GYPCORE

FIRE & MOISTURE RESISTANT  
PLASTER BOARD





## GYPCORE FMR FIRE&MOISTURE RESISTANT PLASTERBOARD

GYPCORE FMR brings together the advantages of two boards; fire and moisture resistance. GYPCORE FMR is the excellent choice for ceilings, partitions and wall-linings in areas prone to both high humidity and fire.



Length (mm)	Indian standard 1830 - GCC standard 2400 on request: any size between 1800 - 3500
Width (mm)	Indian standard 1220 - GCC standard 1200 ask our team for special width sizes
Thickness (mm)	standard 12.50 on request: 7 / 8 / 9 / 9.5 / 12 / 15 / 18
Edge	Tapered: the standard convenient type on request: Squared / Beveled / Round
Color	Face: Green - Back: Grey

Properties (per 12.5mm)	ASTM 1396:2006 Specifications	DIN EN 520:2004 Specifications	GYPCORE FMR Specifications
Flexural Strength (N)Longitudinal	≥ 480	≥ 550	≥580
Flexural Strength (N)Transverse	≥ 175	≥ 210	≥240
Nail Pull Resistance (N)	≥ 343	-	≥348
Core Hardness (N)	≥ 49	-	≥80
Core end Hardness (N)	≥ 49	-	≥80
Edge Hardness (N)	≥ 49	-	≥80
Thickness (mm)	± 0.40	± 0.5	± 0.2
Board Length (mm)	± 6.0	0, - 5	0, - 2.0 mm
Board Width (mm)	0, -3.0	0, -4	0, -2.0 mm
End Squareness (mm)	±3.2	≤ 2.5	± 2.0
Weight (kg/m <sup>2</sup> )			8.5 ± 0.2
Water Absorption	≤5.0%	H-1, H-2, H-3	4.5%
Surface Water Absorption	≤1.5%	-	1.04%